



The OKO-22M-EMA ultrasonic flaw detector is an independent electronic device and is designed for application in stationary high-performance systems (automated multi-channel NDT Systems), transportable systems (mechanized NDT systems) or for manual testing.


Due to the flaw detector is designed in a form of a standalone device with the connection to the PC via Ethernet port, several EMA channels can be connected to the PC via Switch unit. This allows to create EMA multi-channel testing systems.





OKO 22M-EMA software is a universal basic interface for the system setup, testing, viewing and analyzing the saved data irrespective of the purpose of the system, which comprises the integrated multi-channel OKO-22M-EMA flaw detector. Along with the basic software package, the delivery set can also include the numerical data and possibility of setting all channel parameters in a convenient format via Eth. UDP/IP for working in LabVIEW and other environments.

OUTER APPEARANCE OF OKO-22M-EMA PROGRAM INTERFACE



- A) Detection of flat bottom hole with dia. 2 mm at a depth 136 mm (EMAT- 0° 4 MHz, testing the 140 mm bar);
- B) Detection of groove with a depth 0.5 mm and length 10 mm (EMAT- 45° 2 MHz, testing the 140 mm bar)

APPLICATION OF EMA TESTING TECHNIQUE IN VARIOUS INDUSTRIES:

Production sector, test object	Regulatory Documentation	Required number of channels	Operating frequency, MHz	Special requirements
Metallurgy, testing the flat rolled steel	EN10160, ASTM 578/A578M-96, A435A, ISO 12094	60 - 100	2 - 3	Test object temperature can reach to 650 °C
Metallurgy, testing the flat rolled steel bars	EN 10308, EN 10228-3, ASTM E - 2375, MS-STD - 2154	3 - 20	2 - 4	Operating gap is 1 mm, testing velocity is 2 m/s
Metallurgy, testing the slabs	-		0,5; 2; 4;	Operating gap is 0.3-1 mm, testing velocity is up to 2 m/s
Engineering, testing the pipe welded joint	API 5L, API 5 CT, EN 10246-17	12	2 - 4	Operating gap is 1 mm, velocity is up to 1 m/s
Engineering, testing the pipe body, thickness gauging	API 5L, API 5CT, EN 10246, ASTM E1816-96	56	2 - 4	Operating gap is 1 mm, velocity is up to 1 m/s

APPLICATIONS

INTEGRATED INLINE SOLUTIONS

The list below covers the most common and specific NDT applications that require specific instrumentation.

MACHINE BUILDING. TESTING OF WHEEL PAIRS AND ROLLERS High-productivity testing of roll surfaces for the presence of surface and sub-surface flaws is performed due to creeping surface waves in the Pitch-Catch mode. High sensitivity of testing is ensured by Rayleigh waves emission in the frequency range from 0.2 to 1 MHz.










METALLURGY.
TESTING OF SLABS
AND ROLLED PRODUCTS
WITH ROUGH SURFACE

Due to the minimum impact of surface quality on the sensitivity of ultrasonic testing while using the EMA technology, the systems for non-destructive mechanized and automated testing of slabs, plates and bar sections can be designed on the basis of OKO 22M-EMA. The possibility to combine up to 100 channels into one network ensures the performance of high-productivity ultrasonic dry testing in a production flow. The advantage of EMA is testing of objects with high surface temperature.











METALLURGY.
TESTING OF STEEL
STRIPS DURING
PRODUCTION



OKO-22M-EMA system provides for high-speed automated testing of thin steel strips for the presence of internal and surface flaws, such as laminations, laps, inclusions, by ultrasonic non-contact method using a pair of special-purpose angle beam EMA probes, which induce Lamb waves in an object under test. **OKO-22M-EMA** ensures the stable detection of flaws, which, in terms of their reflectivity, are equivalent to the reference reflector of through-hole drilling type with the diameter of 0.8 mm.



METALLURGY.
IN-LINE ULTRASONIC TESTING
OF ERW PIPES ON WELDING
MILL DURING PRODUCTION

OKO-22M-EMA electronics provides for inspection of ERW pipes larger than 60 mm in diameter immediately after welding, along with a superior return on investment by minimizing scrap rates while meeting all the quality codes. The System can be installed directly after a welder to provide immediate feedback on the quality of the weld without quenching. It also provides for a complete volumetric inspection of the weld according to the most stringent API standards.



METALLURGY. ULTRASONIC TESTING OF RAILS ON MILL DURING PRODUCTION

During acceptance testing of rails manufactured in accordance with GOST P 51685, EN13674:1 2011 and TU 0921_231_01124323, **OKO 22M-EMA** provides EMA dry ultrasonic testing of rails.









TRANSDUCERS SPECIFICATIONS

Catalog Fronumber	equency, MHz	Probe angle, º	Working surface size, mm	Connector type	Connector position
EMAT0.5-0	0.5	0	20 x 20	2Lemo00/BNC	cable
EMAT0.5-90	0.5	90	20 x 20	2Lemo00/BNC	cable
EMAT1-0	1.0	0	20 x 20	2Lemo00/BNC	cable
EMAT1-45	1.0	45	20 x 20	2Lemo00/BNC	cable
EMAT1-90	1.0	90	20 x 20	2Lemo00/BNC	cable
EMAT2-0	2.0	0	20 x 20	2Lemo00/BNC	cable
EMAT2-45	2.0	45	20 x 20	2Lemo00/BNC	cable
EMAT2-90	2.0	90	20 x 20	2Lemo00/BNC	cable
EMAT4-0	4.0	0	20 x 20	2Lemo00/BNC	cable
EMAT4-45	4.0	45	20 x 20	2Lemo00/BNC	cable
EMAT4-90	4.0	90	20 x 20	2Lemo00/BNC	cable
EMAT5-0	5.0	0	20 x 20	2Lemo00/BNC	cable
EMAT5-45	5.0	45	20 x 20	2Lemo00/BNC	cable
EMAT6-0	6.0	0	20 x 20	2Lemo00/BNC	cable
EMAT8-0	8.0	0	20 x 20	2Lemo00/BNC	cable

^{*} Working surface size and dimensions of EMA probes can be performed at the customer`s request. Available high temperature EMAT modification.

OKO-22M EMA MAIN SPECIFICATIONS						
PARAMETER VALUE		QUIPMENT OKO-22M-EMA PRO				
PULSER						
• Initial pulse filling frequency 0.5, 1, 2, 3, 4, 5, 6 MHz; (Up to 8 MHz available as an extra option. Selection of a frequency filling is determined by the testing task.);	+	+				
• Type of initial pulse Toneburst Waveform;	+	+				
• Number of periods 2 – 6;	+	+				
Pulser amplitude up to 4000 Vpp;	+	+				
• Pulse energy depends on a filling frequency;	+	+				
Pulse repetition frequency (PRF) from 50 to 2000 Hz.	up to 1000	2000				
RECEIVER						
• Gain adjustment: — 28 dB to 68 dB (gain step 0.1, 0.5, 1, 2 dB);	+	+				
• Filter 0.5, 1, 2, 3, 4, 5, 6, MHz; (Selection of the filter frequency is determined by the testing task.); _	+	+				
• Delay from 0 to 1000 mm in steel (sound velocity 3230 m/s); +	+					
• Range from 1 to 1000 mm in steel (sound velocity 3230 m/s); +	+					
• Namber of averages 2 / 4 / 8 / 16 / 32;	+	+				
• Data presentation A-Scan; B-Scan; C-Scan;	+	+				
TCG						
Depth entire gain range;	+	+				
Number of points not less than 20;	+	+				
 Minimum time step between TCG points up to 1 μs; 	+	+				
• Maximum slope not less than 46 dB/μs;	+	+				
GATES						
Two independent gates per channel Amplitude and time measurements	+	+				
Two acceptance levels per gate	+	+				
A/D CONVERTER						
• 10 bit, 80 MHz	+	+				
PORTS (for communication with PC and various peripheral devices)						
Ethernet (for communication with PC);	+	+				
CONNECTORS						
2 lemo00 connectors for connecting the EMAT to the receiver of EMA channel;	+	+				
1 BNC connectors (one connector for the first pulser, second connector for the second pulser);	+	+				
1 lemo connector for one axis Encoder connection;	+	+				
1 Ethernet connector for transmitting the data to PC;	+	+				
 1 Trigger connector is used either for synchronization between EMA channels, or for EMA channel metrological verification. 	+					
IP LEVEL						
Ingress Protection Rating	IP65	IP44				